



## SIAHFAM BITUMEN PRODUCTS CO

### BITUMEN MC 250

Characteristic	Value	Test Method
Kinematic Viscosity@ 60°C (cSt)	250-500	ASTM D-2170
Flash Point (top open cup) (°C)	66 min	ASTM D-3143
Water Content (%vol)	0.2 max	ASTM D-95
<b>Distillate, %volume of total distillate to @ 360°C:</b>		
to 225°C	10 max	ASTM D-402
to 260°C	15-55	ASTM D-402
to 316°C	60-87	ASTM D-402
Residue from Distillation to 360°C (%Vol by difference)	67 min	ASTM D-402
<b>Test on Residue from Distillation</b>		
Penetration @ 25°C (dmm)	120-250	ASTM D-5
Ductility @ 25°C (cm)	100 min	ASTM D-113
Solubility in Trichloroethylene (%wt)	99 min	ASTM D-2042

\*American Association of State Highway Officials