



SIAHFAM BITUMEN PRODUCTS CO

BITUMEN MC 3000

Characteristic	Value	Test Method
Kinematic Viscosity@ 60°C (cSt)	3000-6000	ASTM D-2170
Flash Point (top open cup) (°C)	66 min	ASTM D-3143
Water Content (%vol)	0.2 max	ASTM D-95
Distillate, %volume of total distillate to @ 360°C:		
to 225°C	---	ASTM D-402
to 260°C	0-15	ASTM D-402
to 316°C	15-75	ASTM D-402
Residue from Distillation to 360°C (%Vol by difference)	80 min	ASTM D-402
Test on Residue from Distillation		
Penetration @ 25°C (dmm)	120-250	ASTM D-5
Ductility @ 25°C (cm)	100 min	ASTM D-113
Solubility in Trichloroethylene (%wt)	99 min	ASTM D-2042

*American Association of State Highway Officials