



Bitumen 60/70	SPECIFICATION	TEST METHOD
Specific gravity 25/25 C	1.01-1.06	D-70
Penetration @ 25 C	60/70	D-5
Softening point C	48/56	D-36
Ductility @25 C	100 MIN	D113
Loss on Heating (WT)%	0.2 MAX	D-6
Drop in penetration after heating %	20 MAX	D-6%& D-5
Flash Point C	250 MIN	D-92
Solubility in CS2 (WT)%	99.5 MIN	D-4
Spot Test	NEGATIVE	* A.A.S.H.O.T.102
*AMERICAN ASSOCIATION OF STATE HIGHWAY OFFICIALS		